

Specialty Grades

Direct Thermal Products & More!

No BPA Added To Any KSP Products.



As part of the OJI group's international network of companies and manufacturers, Kanzaki and its customers enjoy access to a variety of unique and cost-effective imported paper grades. This includes direct thermal label and POS, and direct thermal film. Our sales and customer service team can work closely with your organization to identify imported solutions, navigate logistics and ensure inventory accessibility.

MANUFACTURER	GRADE NAME	CATEGORY	SUBSTRATE	TOP-COAT	CALIPER		BASIS WEIGHT		BRIGHTNESS	SMOOTHNESS	SENSITIVITY	MAX PRINT SPEED	DURABILITY	NO BPA ADDED
OPE BRAZIL	NTC70	Label	PAPER	NTC	3.03 mils	77 µm	70.0 (g/m ²)	18.5#	86%	290 Bekk sec	STD	6 IPS	MED	X
	KPH AF 48	POS	PAPER	NTC	1.96 mils	50 µm	48.0 (g/m ²)	12.8#	90%	260 Bekk sec	STD	6 IPS	SHORT TERM	X
OIM JAPAN	KPT3380P	Film	PP-FILM	TC	3.46 mils	88 µm	70.5 (g/m ²)	18.7#	91%	1.80 µm	HIGH	10 IPS	ULTRA	X
	KPT3370P	Film	PP-FILM	TC	3.07 mils	78 µm	60.8 (g/m ²)	16.2#	90%	1.60 µm	HIGH	10 IPS	ULTRA	X
	POLYCASH	Film	PP-FILM	TC	10.43 mils	265 µm	287 (g/m ²)	76.0#	82%	2.30 µm	HIGH	10 IPS	ULTRA	X



For more information about our global network of affiliated manufacturers and available products, please contact your sales representative, or visit www.kanzakiusa.com

- **Durability:** Environmental resistance depends on thermal chemistry, the degree to which the image was originally developed, and whether a protective topcoat is present. Image life may be reduced by exposure to heat, humidity, excessive light or contact with chemicals such as plasticizers, oils, solvents, adhesives, water and some printing inks.
- **Shelf Life:** (before imaging) The shelf life of Kanzaki direct thermal imaging papers is three years from the date of shipment, when stored under the following conditions: Temperature 68°F ± 9°F (20°C ± 5°C), relative humidity 60% ± 10%, stored in a dark location away from natural and artificial light.



Data represents product averages and does not constitute a warranty.
Vendor shall not be responsible for liability resulting from any deviation from this information.
All products should be pretested to determine suitability for any specific purpose.